emico syskomp group

Material Data Sheet PVC (Polyvinyl chloride)

General information:

Due to its high softness plasticised PVC is very suitable for bumpers, washers and plug-in feet. It can be glued very well.

Physical properties:

Property	Value	DIN
Density (gr/cm ³)	1.4	
Tensile strength (MN/m²)	2971	53455
Elongation at break (%)	400	53455
Modulus of elasticity (MN/m²)	20	53457
Notched impact strength (kJ/m²)		53453
Ball indentation hardness (MN/m²)	Shore A 70	53456
Continuous operating temperature (max °C)	80	
Volume resistivity (Ω.cm)	10^10	53482
Dielectric dissipation factor tan: (10 ³ Hz)	0.1	53483
Dielectric strength (MV/m)	30	53481
Coefficient of friction (compared with) ()		

Chemical resistance:

Resistance to

Benzine	+	Weak lyes	+
Benzol	-	Strong lyes	+
Mineral oils	0	Weak acids	+
Vegetable oils	0	Strong acids	0

syskomp gehmeyr GmbH - emico

Max-Planck-Str. 1 | DE-92224 Amberg *t* +49 9621 67545-0 *f* +49 9621 67545-99 *email* verkauf@emico.de *website* www.emico.de

Important note:

The information about the nature or usability of materials or products is for information only and does not represent a contractual obligation. The information only corresponds to the experience of the manufacturers. All information is provided without warranty. Subject to typing errors, mistakes and changes.