

General information:

Anti-slip polyurethane, provided with an acrylic sub-layer for a strong hold on metal, polycarbonate, ABS and acrylic.

Physical properties:

Property	Value	DIN
Density (gr/cm ³)	1.26	--
Tensile strength (MN/m ²)	50	--
Elongation at break (%)	600	--
Modulus of elasticity (MN/m ²)	25	--
Notched impact strength (kJ/m ²)	--	--
Ball indentation hardness (MN/m ²)	Shore A 70	--
Continuous operating temperature (max °C)	80	--
Volume resistivity (Ω.cm)	--	--
Dielectric dissipation factor tan: (10 ³ Hz)	0.1	--
Dielectric strength (MV/m)	20	--
Coefficient of friction (compared with) (--)	0.15-0.4	--

Chemical resistance:

Resistance to

Benzine	+	Weak lyes	+
Benzol	+	Strong lyes	-
Mineral oils	+	Weak acids	0
Vegetable oils	+	Strong acids	-

Important note:

The information about the nature or usability of materials or products is for information only and does not represent a contractual obligation. The information only corresponds to the experience of the manufacturers. All information is provided without warranty. Subject to typing errors, mistakes and changes.