

General information:

A very elastic material which allows deformations. Usually available in different hardness grades.
 Very suitable as under surface of anti-slip soles.

Physical properties:

Property	Value	DIN
Density (gr/cm ³)	0.92	--
Tensile strength (MN/m ²)	11	53455
Elongation at break (%)	500	53455
Modulus of elasticity (MN/m ²)	--	53457
Notched impact strength (kJ/m ²)	--	53453
Ball indentation hardness (MN/m ²)	--	53456
Continuous operating temperature (max °C)	110	--
Volume resistivity (Ω.cm)	10 ¹⁶	53482
Dielectric dissipation factor tan: (10 ³ Hz)	--	53483
Dielectric strength (MV/m)	--	53481
Coefficient of friction (compared with) (--)	--	--

Chemical resistance:

Resistance to			
Benzine	0	Weak lyes	+
Benzol	-	Strong lyes	+
Mineral oils	+	Weak acids	0
Vegetable oils	+	Strong acids	-

Important note:

The information about the nature or usability of materials or products is for information only and does not represent a contractual obligation. The information only corresponds to the experience of the manufacturers. All information is provided without warranty. Subject to typing errors, mistakes and changes.